RECENT DEVELOPMENT AND CHALLENGES IN SYNTHESIS OF CELLULOSIC NANOSTRUCTURES AND THEIR APPLICATION IN DEVELOPING PAPER-BASED ENERGY DEVICES

FIROOZEH DANAFAR

Department of Chemical Engineering, Faculty of Engineering, Shahid Bahonar University of Kerman, Kerman, Iran ⊠ Corresponding author: danafar@uk.ac.ir

Received August 25, 2019

Cellulose can be extracted from different natural sources, including plants, marine animals, or microorganisms. Nanocellulose (NC) can be then produced from it, in the form of either crystal or fiber, depending on the source of cellulose and process conditions. In the last decades, the interest in the application of NC as a building block in functional composites has significantly increased. Such a trend will keep growing due to the exceptional properties and sustainability of NC. Paper energy devices have been developed for various applications, especially those related to harvesting and saving energy. This article first briefly reviews the fundamentals related to the NC and its synthesis, and then describes thoroughly the functionalities provided by paper-based energy devices. Although these functionalities bring a great opportunity to develop new value-added products, there are several challenges in the way of commercialization of paper-based electronic and electrical devices. These challenges are summarized to open up avenues of further research, in addition to providing novel ideas for developing such devices.

Keywords: nanocellulose, cellulose, paper-based energy devices

INTRODUCTION

Developing low-cost and renewable resources is important to meet up the energy demands and resolve the environmental problems associated with the disposal of electronic and electrical devices. Currently, the major portion of the global energy demand is supplied by fossil fuels, which are limited resources. Besides, fossil fuels have low efficiency of power generation and cause air pollution. Finding a sustainable manner to supply energy by using clean fuel derived from renewable resources of energy has become a global initiative. The major problem concerned with renewable resources of energy, like solar and wind, is that they are periodic, thus the energy comes in pulses rather than in a steady stream. Developing eco-friendly power sources and storing energy in batteries, capacitors and fuel cells can help solve this problem. Replacing the metals used in these devices with naturally decomposable conductive composites will help reduce tons of CO_2 emission. The increase of electronic wastes, which are not naturally decomposable, is also one of the major environmental concerns noted these days. New insights into developing conductive biopolymers, which are environmentally friendly, encourage researchers to focus on using natural polymers, such as cellulose, chitosan, starch *etc.* Cellulose, as the most abundant sustainable resource, is extensively under survey for developing a new generation of electronic and electrical devices.

Cellulose, a fascinating biopolymer, is widely distributed in the nature in plants, microorganisms and some animals. Independently of its source, cellulose is a linear polymer of D-anhydroglucopyranose units linked together by β -1,4-glucosidic bonds. Any physical or chemical modification of the cellulose chain will change its molecular structure and thus such a versatile structuring of cellulose has enabled its diverse applications (*e.g.*, as a filler in novel functional materials, coatings and laminates, paper electronics, smart textiles, optical films, sorption media and viscosity regulators). The application fields of cellulose tend to extend, as it is anticipated that the world market of cellulose nanostructures will reach about 37 billion dollars in 2020.¹

The application of cellulosic structures in the energy sector has been extensively studied for biofuel production.²⁻⁴ Moreover, cellulosic materials can be effectively used in developing biocompatible products as a replacement of petroleum-based plastics. These materials also are excellent for fabrication of energy-efficient devices, such as paper batteries, super-capacitors, insulators, paper

displays, electric heaters and antistatic coatings.⁵ Cellulosic nanostructures have several advantages in developing biocompatible composites and paper-based energy devices due to their supreme physical and chemical properties. The superiority of cellulosic nanostructures, compared to other widely used nanostructures, such as fullerenes and carbon nanotubes, lies in their biodegradability, renewability, sustainability, abundance and high biocompatibility.

Nanocellulose can be produced in the form of either crystal or fiber, depending on the source of cellulose and process conditions. Nanostructures have unique reinforcing properties, including high elastic modulus, high specific strength, high elasticity, dimensional stability, and low thermal expansion coefficient.⁶ These properties, along with the low density and high aspect ratio, make NC attractive to be used as reinforcing element in composites. The high surface area of NC also makes it a strong adsorbent. Moving to the nanometer scale, some exceptional properties appear. For example, cellulose is known as an insulating material, while NC is conductive and transparent. The reason for these unique optical properties of nanocellulose lies in its nano-size, being on the same scale as the critical size for light transmission.

Despite its diverse applications, the efficient separation of cellulosic nanostructures is a major challenge, limiting the wide utilization of these renewable components. The morphology and hence the properties of regenerated cellulose depend on the source of cellulose, the technique and the operation conditions used.⁷ For instance, depending on the substrate and pretreatment steps, the regenerated cellulose can be transparent or opaque. The source of cellulose also determines some important properties and characteristics, such as shape and size distribution of crystalline nanoparticles and their aspect ratio.⁸⁻⁹ The current paper aims to review the recent advancements in the extraction of cellulosic nanostructures, as well as to present recent progress in the development of energy and electronics devices using NC. Before going into the applications of NC, it is necessary to provide a brief explanation on the cellulose structure and its extraction techniques.

CELLULOSE SOURCES

Cellulose is the most abundant natural polymer derived from biomass, including plants, some sea animals, and microorganisms (Fig. 1). Despite the similar structure, the cellulose derived from each source has several different characteristics. The following paragraph presents the characteristics of cellulose extracted from different sources.



Figure 1: Different sources of cellulose



Figure 2: Hierarchical structure of cellulose and its nano-sized types (with permission¹²)

Cellulose from plants

Plants or agricultural wastes, including woody or non-woody plants, such as cotton, hemp, jute and sisal, as well as sea grass species, such as *Posidonia oceanic*, are the major source of cellulose. The tubular structure of the cell wall in plants comprises a helically wound arrangement of cellulose nanofibers with a width of 1.5-3.5 nm and length of 1 μ m and above.¹⁰ These nanofibers, mostly known as cellulose microfibrils, consist of a semi-crystalline structure embedding cellulose molecular chains. In the crystalline domains, the long chains of cellulose are connected by hydrogen bonds and form a highly ordered crystalline structure. The amorphous region of cellulose in plants usually consists in hemicelluloses and lignin, and sometimes pectin. The properties of cellulose extracted from plants depend not only on the treatment methods applied, but also on the plant source and the plant part used.^{6,11-12} Depending on the synthesis approach, natural cellulose can be transformed into different nanostructures, such as crystals or fibrils (Fig. 2).

Cellulose from microorganisms

In addition to plants, several microorganisms can be used to produce cellulose, either *in vivo* or *in vitro*.¹⁴⁻¹⁵ For instance, cellulose has been found in some classes of green algae, such as *Chlorophyceae, Valonia ventricosa* (also known bubble algae), *Chaetamorpha melagonicum*, and *Glaucocystis*. Although the cell wall of most fungi consists of chitin, several fungi, namely, *Acytostelium, Dictyostelium* and *Polysphondylium*, have cellulose in their cell wall. Bacteria belonging to the genera *Gluconacetobacter* (or *Acetobacter*), *Agrobacterium, Pseudomonas, Rhizobium* and *Sarcinacan* can synthesize cellulose from the carbon sources (like glucose) existing in their culture media. Amongst the cellulose-forming bacteria, a non-pathogen, gram-negative bacterium *Gluconacetobacter*, which secretes the cellulose into the culture medium, is suitable for economical production of bacterial cellulose.¹⁶⁻¹⁸

Bacterial cellulose is a fibrous network with a high degree of polymerization (up to 10,000), as well as high crystallinity (70-80%) and purity (no lignin, hemicelluloses, pectin, or other biogenic products).¹⁸⁻²⁰ These characteristics make bacterial cellulose an appropriate material to be used in electronics, acoustics, and biomedical devices. Bacterial cellulose has been used to develop hydrogels, due to its large surface area and hydrophilic nature. However, due to its low compressive modulus, the water is easily squeezed out of the gel under slight compression.¹⁴ Despite all the exceptional features of bacterial cellulose, its production requires special care and handling to maintain optimal production.

Animal cellulose

Cellulose can be also found in the outer membranes of some marine animals, like Ascidians, known as tunicates or sea squirts. The cellulose that reinforces the proteins of the outer membrane of Ascidians can be obtained through bleaching treatments of the protein.^{21,22} The cellulose nanostructures derived from tunicates exhibited higher crystallinity and aspect ratio, compared to NC obtained from bacteria.⁸ However, cellulose from marine animals is of little commercial interest because of its lower availability.

CRYSTALLINE STRUCTURE OF CELLULOSE

Several polymorphs of cellulose are known to exist, called cellulose I, II, III and IV. They all differ in the dimension of the unit cells, number of chains included in the crystal unit cell, orientation of the chains in the crystal (parallel or antiparallel) and chain polarity. Almost all natural celluloses consist of cellulose I, which is a composite of two crystalline allomorphs, labeled as I_{α} and I_{β} .²⁰ The conversion between these allomorphs generally occurs under hydrothermal conditions, when the hydrogen bonds between cellulose sheets are splitted.^{23,24} Cellulose obtained from algae (*e.g. Valonia*) and bacteria (e.g. G. xylinum) is predominantly cellulose I_{α} , whereas plant cellulose is mostly cellulose I_{β} . The crystalline cellulose I_{α} is thermodynamically metastable, while I_{β} is more stable.⁷ Partial conversion of cellulose I_{α} to I_{β} happens by its annealing at a temperature higher than 250 °C. This conversion is irreversible.²⁰ Cellulose II is known as the most stable crystalline structure of cellulose. It is formed naturally by a mutant strain of *Gluconacetobacter xylinum* and the alga *Halicystis*. Also, it can be obtained by the treatment of cellulose I via regeneration (dissolved and precipitated) and/or mercerization (treated with a strong alkaline swelling agent ($\sim 20\%$) and washed with water).⁷ The transformation of cellulose I to cellulose II is irreversible. Cellulose III, a fairly stable polymorph, is formed by treating cellulose I or II with liquid ammonia at a temperature below -30 °C, or with amines, followed by removing the swelling agent anhydrously, for example, by washing with alcohol. Depending on the cellulose polymorph (I or II), two subclasses (III_I and III_I), with small differences in the lattice dimensions of the crystals, are formed.⁷ Cellulose IV is formed by annealing of cellulose III in a suitable liquid, for example glycerol, at high temperature and under tension.¹⁰ The structure of cellulose III_{II} and cellulose IV is still a matter of debate. Cellulose IV_I is known as the disordered form of cellulose I.

Several characterization techniques have been used to study the crystalline structure at the subnanometer level. These techniques include neutron diffraction (ND), X-ray diffraction (XRD), infrared spectroscopy (FTIR), Raman spectroscopy, nuclear magnetic resonance (NMR), and vibrational sum frequency generation (SFG). Each technique can provide specific information that can be used for differentiation of the polymorphs. Table 1 presents information about the structure of the cellulose polymorphs and their characteristics obtained by XRD, FTIR or NMR methods. The final characteristics of cellulose nanostructures depend not only on the source of cellulose, but also on its treatment procedure or method of production. Common treatment techniques used for cellulose fibrillation will be presented in the following section.

OVERVIEW OF SYNTHESIS METHODS

Depending on the source of NC (plants, microorganism or animal), the synthesis approach is different. Due to their availability, plants are the most widely investigated source for NC production. The top-down approach, including mechanical, chemical and biochemical extraction procedures, has been used to produce NC from plant sources. Cellulose production from microorganisms and/or animals is a bottom-up approach, which has also attracted attention recently. Accordingly, this section focuses on NC production from plants and bacteria.

Polymorph	Chain characteristics	XRD ²⁵⁻²⁹		FTIR ²⁸⁻³⁰		
		Bragg's angle	Miller index	peaks at (cm^{-1})	NMR ²⁹⁻³¹	
I_{α}	One-chain triclinic Parallel	14.3-14.5 16.3-16.9 22.5-22.9 34-34.4	100 010 110 11 4	750 3240	Double peaks in C4 region The 2 nd peak in the down-field site at 89.7 ppm	
I_{β}	Two-chain triclinic Parallel	14.5-14.9 16.5-16.7 22.5-23 20.6 34.5	1 1 0 110 200 102 004	710 3270 3340	C-6 chemical shift at 64.8-64.9 ppm Double peaks in C4 region The 2 nd peak in the up-field site at 88 ppm Double peaks in the C1 region around 106 ppm	
Π	Two-chain monoclinic Antiparallel	12-12.2 20 21.8-22.1 34-37	1 1 0 110 020 004	3450 3480-3484	C-6 chemical shift at 62.2- 62.8 ppm Double peaks in the C1 region Double peaks in the C4 region	
IIII	One-chain monoclinic Parallel	11.7 17.2-17.3 20.7-21.1	010 002 100 012 1 10	3480	C-6 chemical shift at 62.1-62.2 ppm	
III _{II}	Still being debated Antiparallel	11.7 20.7-21.1	010 100 012 1 1 0	3450 3480	C-6 chemical shift at 62.4-62.5 ppm	
IVI	Disordered form of cellulose I Parallel	NR*				
IVII	Still being debated Antiparallel	15.5 15.5 20 22 35	1 1 0 110 012 020 004	NR	C-6 chemical shift at 63-63.6 ppm	

 Table 1

 Cellulose polymorphs and their characteristics

* NR - not recorded

Cellulose from plants – a top-down approach

The amorphous and crystal parts of cellulose in plant cell walls are sequentially located along the fiber direction in a row. The amorphous parts can be easily broken, while breakage of the crystal parts is impossible due to the presence of strong hydrogen bonds between the hydroxyl groups in cellulose. The production of cellulose nanostructures from natural resources is not an easy task because there are a variety of plant sources with different composition. Depending on the synthesis approach, natural cellulose can be transformed into different nanostructures, such as crystals or fibrils.

The production of cellulose nanostructures from plant sources, including wood, non-wood plants, agricultural crops, and agricultural wastes, is generally a multi-stage process. A pretreatment of natural sources is usually required to disrupt the lignin structure, delaminate the cell wall and obtain individual cellulosic fibers. Depending on the plant source of the cellulose, the pretreatment method, which facilitates access to the micro-sites of cellulose during the next stage, is selected. For instance, agricultural crops and by-products contain less lignin than wood. A proper selection of the pretreatment procedure will increase the accessibility to the micro-sites of cellulose, while maintaining a desired degree of its polymerization. Cellulosic fibers are further processed to break the amorphous parts of cellulose and extract the cellulose nanostructure. The size and type of the nanostructure formed, *i.e.* nanofiber, nanocrystal or nanowhisker, depends not only on the source of the cellulose, but also on the procedure used. There are three distinct approaches used in a route to extract cellulose

nanostructures from plant sources: mechanical treatment, chemical treatments and biochemical treatment, which is enzymatic hydrolysis. A combination of these techniques is usually applied, improving the fibrillation and thus NC extraction.

Mechanical extraction methods

Mechanical treatments that subject natural fibers to high shear forces enable cellulose fibrillation. Mechanical processes used to extract cellulose include mainly refining and high-pressure homogenization, grinding, cryocrushing and high intensity ultrasonic treatments.

Homogenization

In a homogenizer, a dilute suspension of cellulose is pumped at high pressure through a springloaded valve to pass through a thin slit. The quick reciprocating motion of the valve subjects the fiber to a large pressure drop and high shearing forces. The degree of defibrillation directly depends on the pressure and number of recycles. Repeated high-pressure homogenization of diluted cellulose slurry promotes fibrillation of the cellulosic fibers.^{32,33} The pressure as well as homogenization cycles also influence the characteristics of cellulose nanostructures, including their diameter and crystallinity.³⁴ The degree of cellulose defibrillation depends on the polarity and swelling properties of the liquid, which the cellulose fibers are dispersed in. Any polar liquid can be used to prepare the cellulose suspension; however, the aqueous suspension of cellulose is preferred. Besides the parameters mentioned, the dimension and design of the homogenizer chamber requires precise consideration. An important issue is the agglomeration of cellulose fiber that blocks the narrow slit in the device and leads to termination of the process. Besides that, because of the high pressure applied, the chamber must be strong enough to tolerate this level of pressure. Another problem is that an increasing suspension temperature in the homogenizer influences the process yield and product properties. Because of the high-energy consumption of the homogenization process, cellulose fibers are commonly pretreated by other techniques to reduce the energy consumption and promote the process efficiency. 32,35-39

Microfluidization

In a microfluidizer, the cellulose slurry is continuously pumped into precisely engineered microchannels within an interaction chamber. The slurry is fed through an intensifier pump, which supplies the desired pressure and pushes the sample at a constant rate into the interaction chamber. The microchannels have a precisely defined fixed-geometry, commonly Z- or Y-shaped, which accelerate the slurry stream to high velocities and impose high shear (up to 10^{-7} s⁻¹). The extremely high shear and impact forces will delaminate the cellulosic fiber to NC. The outlet stream is usually circulated through the chamber to improve the degree of fibrillation and obtain homogeneous particle size distribution.

The geometry of micro-channels, which influence the shear and forces produced, plays a key role in the efficiency of fibrillation and dispersive mixing of the cellulose fibers. Keep in mind that micro-fluids at such high velocity have a complex flow, where the shear rate, shear stress, and boundary conditions cannot be well defined. Consequently, the fluid properties, such as viscosity, and first normal stress difference cannot be assigned a value characteristic of the fluid. Like in the case of homogenization, a pretreatment is necessary in order to enhance fiber accessibility and processing efficiency.⁴⁰⁻⁴²

Grinding process

Grinding is the breakdown of cellulose fibers by applying mechanical shear stress. Two methods of grinding are distinguished: wet and dry grinding. In wet grinding, an aqueous suspension of cellulose fibers is subjected to mechanical shear, whereas in dry grinding no water is present. Dry grinding increases the biomass reactivity without any effluent production, however, its energy consumption for biomass grinding is a limiting factor to be employed at an industrial level. Wet grinding, which consumes less energy, also generates irreversible changes in the fibers, increasing their bonding potential by modification of their morphology and size. Different types of grinders have been employed in NC production.⁴³⁻⁴⁶ The most frequently used grinders are disc mills, planetary ball mills, bead mills, pearl mills, and twin-screw extruders. An ultrafine friction grinder, which is a specially

designed disc mill, was predominately used to fibrillate a dilute slurry of cellulosic fibers.^{43,47} All these studies indicated that the size of NC depends on the round number and speed of grinding. However, after a maximum number of rounds, there is no significant change in the size of NC.

Cryocrushing

The slurry of cellulose fiber is frozen using liquid nitrogen or propane. The fibers are then subjected to high shear forces and the ice crystals formed within the cells exert pressure on the cell walls, causing them to rupture and release microfibrils.⁴⁸⁻⁵¹

Ultrasonication

Ultrasonication is another mechanical method in which hydrodynamic forces disaggregate cellulosic fiber to nanofibers. In this method, ultrasonic waves (typically 20-50 kHz) in aqueous medium create strong mechanical stress because of cavitations and cause defibrillation of cellulose fibers. Ultrasonication is, basically, an assisted method, which is used in combination with chemical/biochemical processes and sometimes with other mechanical methods.^{9,52-58} These studies indicate that the application of ultrasonic waves helps produce cellulose nanostructures. The efficiency of defibrillation in the ultrasonication process depends on the power, concentration, temperature, time and distance from the probe tip used, as well as the dimensions of the source fibers.⁵⁵ Besides its high level of noise and energy generation, free radicals that can react with other molecules may be generated when ultrasound is used to fibrillate the cellulose.

Aqueous counter collision (ACC)

In this technique, a pair of water jets is used to reduce the particle size of materials. The kinetic energy produced by this method can be in the range of 6.7-18.1 kJ/mol. This amount of energy is high enough to disturb the dipole-dipole, London dispersion forces, and weak hydrogen bonds.⁵⁹⁻⁶¹ The characteristics of cellulose nanostructures, including their dimension and the type of crystals, vary as a function of treatment repetition. Research indicated that, by repetition of aqueous counter collision, cellulose I_a was converted to I_b, while it retained its high crystallinity.⁶⁰

Electrospinning

Electrospinning is a method used to prepare cellulose nanostructures through the action of electrostatic forces. Under a voltage adequate to overcome surface tension forces, a jet of cellulose suspension shoots out toward a collector, where the interconnected nanofibers are collected. The effectiveness of this method in defibrillation of cellulose depends on its controlled swelling and dissolution in a liquid phase. In a suitable solvent or swelling agent, the crystalline cellulose can be separated efficiently into nanofibers.⁶¹⁻⁶⁶

Several solvents have been investigated for cellulose, such as N,N-dimethylacetamide (DMAc) with lithium chloride (LiCl),⁶⁷ dimethyl sulfoxide (DMSO)/triethylamine/SO₂,⁶⁸ N-methylmorpholine-N-oxide (NMMO),⁶⁹ aqueous solution of NaOH/urea⁷⁰ and ionic liquids, like 1-butyl-3-methylimidazolium chloride (BMIMCl), 1-allyl-3-methylimidazolium chloride, 1-butyl-3-methylimidazolium hydrogen sulfate or carbon disulfide/aqueous NaOH.^{64-66,71-75}

Whereas the dissolution of cellulose is a key step in this method, an appropriate solvent to dissolve cellulose is difficult to find. In this respect, pretreatment of cellulose has been examined. For instance, since the derivatives of cellulose can be dissolved in many common solvents, especially organic solvents, chemical treatments to obtain a derivative of cellulose, such as cellulose acetate, carboxymethyl cellulose or hydroxypropyl methylcellulose, have been tried. Another approach is using enzymatic pretreatment of cellulose.⁶¹ The result of electrospinning depends not only on the type of solvent (single or binary solvent), but also on the spinning conditions, origin of cellulose, its degree of polymerization and pretreatment methods.⁷⁶

Steam explosion

In this process, the biomass is subjected to high pressure steam (20 bar and higher) at temperature higher than 200 °C for a relatively short time. Depending on the degree of decomposition achieved though steam explosion, a post-treatment procedure to remove the remained hemicelluloses and lignin

is necessary. The effectiveness of steam explosion depends upon the nature of the feedstock and the operation conditions, such as pressure, temperature and process time.^{36,77-79}

Chemical approaches

There are various chemical approaches, such as acid hydrolysis, oxidation, carboxymethylation, acetylation, chlorination and alkaline treatment, used in a route to produce cellulose nanostructures. The aim of these approaches is different and can be either chemical modification of the cellulose surface, improvement of cellulose dispersion, breakage of bonds or removal of undesired components, such as lignin and hemicelluloses.^{11,33,79-81}

Among the mentioned approaches, acid hydrolysis has been widely used as acids can effectively break the amorphous region in natural fiber and release its crystal domains into the suspension. Depending on the plant source of fiber, hydrolysis conditions must be mild enough to avoid conversion of cellulose to glucose. Besides the source of cellulose, processing conditions influence both the process efficiency and product properties.^{12,38,82-88} The processing factors include the type of acid used, its strength, reaction time, temperature and the ratio of acid to cellulose. The mostly used acids have been sulfuric and hydrochloric acids, however, using other acids, such as phosphoric,⁸¹⁻⁸³ hydrobromic⁹²⁻⁹³ and organic acids (like maleic acid),⁹⁴ have been reported. Although all acids can hydrolyze the amorphous domain, they have different power of hydrolysis and they can affect the properties of the reaction environment, as well as the product.⁸⁹ In this respect, acid mixtures have been also examined to improve the process results.⁹⁵⁻⁹⁶ Solid acid catalysts, with Brønsted acid active sites, can be used in the hydrolysis reaction, instead of concentrated acids. However, the contact between the catalyst active sites and cellulose are challenging as both the reactant and the catalyst are in solid phase. Similarly to acids, ionic liquids, introduced as solubilizing agents for cellulose, can also break the glycosidic bonds between the anhydroglucose units in cellulose.^{73,97} Since ionic liquids are not consumed and can be regenerated at the end of the reaction, it is logical to say they act as catalyst.

Oxidation of native cellulose, with the purpose of its surface modification, has been mostly used as a pretreatment step in a route to produce nanocellulose.^{57,98-101} This pretreatment leads to saving energy consumption, especially where the mechanical approach is used to produce nanocellulose. The most used oxidation of native cellulose is catalytic oxidation using TEMPO (2,2,6,6-tetramethylpiperidine-1-oxyl). TEMPO oxidation consists in a selective conversion of the hydroxyl groups in native cellulose to aldehyde and carboxylate functional groups in the aqueous phase and under mild conditions. In TEMPO oxidation, fibers are separated due to the repulsive forces among ionized carboxylates, which overwhelm the hydrogen bonds holding them together.¹⁰² Among the chemical approaches introduced here, acid hydrolysis and TEMPO oxidation are toxic and environmentally incompatible processes, while using ionic liquids facilitates sustainable and green production of nanocellulose.

Biochemical approach

Similarly to chemical hydrolysis, cellulolytic enzymes (specifically, endoglucanase) attack the amorphous regions of the cellulose fibers and make the extraction of NC easier. The major advantage of the enzymatic treatment for NC production, compared to other techniques, is the selective hydrolysis of the amorphous region. This selective hydrolysis caused the cellulose nanostructures produced to have a more favorable structure than those produced by chemical hydrolysis.⁴² Other advantages of biochemical hydrolysis from the environmental point of view are related to that fact that it is less corrosive, involves less loss of material and requires low energy consumption. The immobilization of enzyme can be performed to improve the enzymatic hydrolysis economically. However, the low yield and high cost of enzymatic hydrolysis are important issues that limit its industrial application.^{2,8} In almost all the studies that used enzymatic hydrolysis to produce nanocellulose, this treatment is combined with other methods, mechanical or chemical ones.^{2,35,41,48,103-104}

It is worth mentioning that biochemical treatment must be performed in very aseptic conditions and thus some technical considerations, such as sterilization of the equipment and protection against contaminants, must be taken into account.

Synthesis of bacterial cellulose

Bacterial NC is produced by *Gluconacetobacter* as a part of its carbon metabolism. In addition to glucose and fructose, other carbohydrates, such as manitol, glycerol, sucrose and galactose, can be used as carbon sources in *Gluconacetobacter* culture.¹⁰⁵ Depending on the main carbon source in the growth medium, there are different initial pathways toward the central metabolites. Different pathways produce different amounts of water-soluble polysaccharides, like acetan and levan, which influence the production of cellulose nanostructures.¹⁰⁶ The amount of these water-soluble polysaccharides produced depends on the type of carbon source and bacterial strain, as well as whether the strain is mutant or wild type.

Two production methods, static and agitated, in different cultivation approaches (batch, fed-batch, continuous) have been used to produce bacterial NC. In the static method, a gelatinous layer (up to several centimeters thick) is formed on the surface of the incubation medium, whereas in the agitated culture, irregular spherical grains are obtained.¹⁰⁷ Accordingly, depending on the desired application of cellulose, the cultivation method is selected.

Despite many attempts for the production of bacterial NC, its commercial production is still performed through static cultivation in shallow containers, using minimally automated work processes. For transferring the production of bacterial NC to an industrial scale, the yield and efficiency of the process need to be significantly improved. In this respect, novel and modified bioreactors have been designed. As an example, Song *et al.*¹⁰⁸ modified the airlift-type bubble column bioreactor or Kralisch *et al.*¹⁰⁹ developed a horizontal lift reactor.

Whether the static or agitated production method is used, the applied conditions influence the properties of the obtained nanocellulose, its yield and rate of production.^{105-106,110-115} The production conditions include carbon source and its concentration, process temperature, oxygen supply, and process time. It is worth mentioning that the efficiency of the process, when it involves microorganisms, also depends on how well the equipment is sterilized and protected against contaminants.

PROPERTIES AND APPLICATIONS OF CELLULOSE NANOSTRUCTURES

Nanocellulose, which is smooth, transparent, mechanically strong and thermally resistant, allows creating durable and flexible paper-based energy devices.¹¹⁶ It contains three hydroxyl groups, which are highly active and useful for chemical modification.¹⁰ This section explains how these characteristics are involved in developing paper-based energy devices. Minimization of thermal effects on the device is one of the main requirements for its performance. Thermal stability of the materials determines the temperature range for material processing, as well as the final characteristics of the product and its usage. For instance, melt processing requires high temperatures, and hence this method cannot be applied for materials with low thermal stability. Smart devices and sensors also require reliable thermal isolation between the sensing elements and the sensor substrate. Besides, poor thermal stability limits the layer thickness of the paper, while the paper thickness affects the performance of the device. Thin and strong papers are suitable to be used not only as a reinforcement element, but also as a binding material in energy storage applications. For instance, a thin separator is preferred for supercapacitors, as it provides the maximum capacitance for them.¹¹⁷ It is worth mentioning that the thermal characteristics of nanocomposites depend not only on the nanocellulose, but also on the other components (especially the polymer), as well as on good dispersion of nanocellulose and its compatibility with the other components.

Cellulose nanocrystals exhibit a very low thermal expansion coefficient (TEC), ranging from 0.5×10^{-5} K⁻¹ to 17×10^{-5} K⁻¹, depending on their polymorphism and surface chemistry.¹¹⁸ It has been reported that, unlike the cellulose nanocrystals, which showed a linear TEC, the composite containing nanocellulose exhibited almost no thermal expansion or contraction. The TEC for the nanocomposite made of nanocellulose was reported lower than that for cellulose nanocrystals (about 10^{-7} K⁻¹).¹¹⁸ This value is lower than the TEC of metals, which is about ~ 10^{-6} K⁻¹. Because of the low TEC of nanocellulose, paper-based energy devices exhibit high resistance to thermal shock and thermal deformation. The strength of interactions in the polymer-nanocellulose network needs to be strong enough to restrict the TEC of the composites.

Besides their favorable thermal properties, cellulose nanostructures indicate good mechanical properties, which make them suitable to be used in paper-based energy storage devices. For example,

strong porous films using nanocellulose, in which hydrogen bonds generate inter-fiber contacts, can be fabricated.¹¹⁶ This porous structure allows the ionic species move easily between the electrode surfaces. High elastic modulus (up to 150 GPa) and strength (up to 7 GPa) have been reported for nanocellulose.¹¹⁸ Different values have been reported for the stiffness of nanocellulose, depending on its original source, morphological properties, geometrical dimensions, degree of crystallinity and polymorphism. Besides these inherent characteristics of nanocellulose, the method applied for its production, as well as the measurement method used, caused differences in the reported data.

Interestingly, nanocellulose exhibits different optical response, compared to other cellulosic materials, because of its nanoscale size, anisotropic individual structures and liquid crystalline behavior.¹¹⁸ Cellulose nanocrystals are birefringent, and have refractive indices of 1.618 and 1.544 in the axial and transverse directions, respectively. The optical properties of transparent cellulosic films can be tuned by modifying the precursor liquid crystalline characteristics of the system, as well as by varying the amount of the nanocellulose. Well-dispersed nanocellulose can replace conventional cobinding materials in coatings to improve whiteness, opacity, smoothness, and printing clarity of new papers. Environmentally friendly transparent films made of nanocellulose are a good substitute for transparent plastics in different devices, for example, flexible displays, organic light emitting diodes, transparent insulating, or semiconducting substrates in transparent paper transistors. Paper-based transistors are applicable in disposable microelectronics, such as biosensors, and in intelligent packaging.

PAPER-BASED ENERGY DEVICES IN ENERGY APPLICATIONS

Nanocellulose has been proposed to be used in paper-based devices due to its outstanding properties.^{5,40,116,119-121} The three-dimensional hierarchical structure of nanocellulose and its ability to hold other functional materials open up great opportunities for using cellulose in electrical, electrochemical, optical and energy storage devices.⁵ Paper is generally known as an insulating material. However, it is possible to make it conductive by incorporation of conducting materials, such as metals, or carbon nanostructures (carbon nanotubes or graphene).^{120,122-124}

Conductive papers are fabricated by two different approaches: one in which cellulose is the hostmatrix for additives and the other where, besides additives, cellulose is blended with another polymer. Conductive papers have high flexibility, which makes them suitable for applications where high load or high frequency exists. However, the applications of cellulose are restricted because of its limited functionalities. On the other hand, cellulosic nanostructures, with their exceptional properties (including high aspect ratio, very low density, high thermal stability, chemical resistance, and high mechanical strength), have broadened the development of conductive papers for different applications. Besides, the similarity in dimensions of NC and other nanostructures, such as CNTs, graphene and Cu nanoparticles, allows uniform mixing of the two components in a matrix, which results in highly conductive films. Such films are appropriate for various applications, ranging from energy-efficient devices to smart devices and electronic components (like transistors).^{5,119-120,125-127} The low density of nanocellulose also encourages its usage in the fabrication of portable electronic devices.

Energy storage devices

Energy-efficient devices, in which excess energy can be held for future usage, are now the center of attention. The performance of such devices depends on how the energy is stored. Cellulose, due to its extraordinary structure, is a promising candidate to be used in energy storage systems. The linear chains of plant cellulose aggregate to highly ordered structures, which are fibers at the nanoscale, called nanofibrils. These structured nanofibers are suitable in the fabrication of energy storage devices.

According to the basic operating principles, paper-based devices for energy storage could be categorized as: (i) electrochemical devices, including batteries (in lithium-ion batteries) and electrochemical capacitors (or supercapacitors), (ii) fuel cells and (iii) nanogenerators.

Electrochemical batteries and electrochemical capacitors are two types of energy storage devices that work based on electrochemical processes. They have similar structure, consisting of two electrodes, an electrolyte and a separator. The electrodes are conductive for transporting electrons and ions, and the separator electrically isolates the two electrodes. However, despite their structural similarity, they use different storage mechanisms. In batteries, the electric charge is stored as chemical energy through an electrochemical redox reaction, whereas in supercapacitors the electrostatic charge

is stored through the formation of an electric double layer at the interface between the electrolyte and the electrodes. This difference makes their application different. The battery is generally taken if a large amount of energy is required to be delivered gradually. Whereas, if a powerful burst of energy lasting a short time is needed, the capacitor is used. Supercapacitors are employed in high power applications and batteries in low power applications.

Supercapacitors, due to their high specific capacitance and power density, are typically superior to batteries in the rate of charge/discharge, as well as with regard to their environmental impact and safety. With respect to the weight and volume of the devices, Li-ion batteries have much higher energy densities than supercapacitors. Consequently, Li-ion batteries have found by far the most application markets.¹¹⁹ However, there is a great attempt to enhance the performance of supercapacitors for a wider range of applications. For instance, to make supercapacitors flexible and stretchable, so that they can be used in portable and wearable electronics.¹²⁵⁻¹²⁹ Flexible supercapacitors, due to their high capability, long cycle life, low cost, and easy fabrication, have attracted great attention. Paper-based supercapacitors display much higher specific capacitances than devices based on plastic substrates, as well as excellent cycling performance. Wearable electronics (or smart textiles) are employed in several novel applications, such as high-performance sportswear, wearable displays, new classes of portable power, and embedded health monitoring devices.¹³⁰⁻¹³³ In all these applications, the device is expected to function steadily and hence it must be powered by stable and lasting energy sources. A current approach in fabricating wearable electronics is to create flexible batteries or supercapacitors integrated within a textile matrix.¹³³

Conductive papers, which are flexible and porous, are researched for fabricating energy storage devices.^{119,121,124-125,127-135} In both batteries and supercapacitors, cellulose nanostructures have been investigated to be used as electrodes,^{119,134,136} separators,¹³⁴ and/or electrolytes.^{129,137,138} Conductive papers used as electrodes in energy storage devices showed higher rates of electron transfer, compared to conventional powder and film electrodes. The porous structure of conductive papers provides a desirable surface area that can achieve larger energy and power densities, higher rate capability and longer cycle life. It has been revealed that as the electrode thickness increases, the impedance associated with the ion or electron transport also increases dramatically.¹¹⁹ Therefore, larger internal resistance and potential are generated. These parameters are detrimental to the device efficiency and its stability performance. If cellulosic nanofibers are used in separators of batteries, as they provide a nanoporous structure, the ionic conductivity of a membrane soaked with liquid electrolyte increases. The main advantage of using cellulose nanostructures in fabricating energy storage devices is that they can serve as both electrode materials and separators, which results in developing flexible and thin devices. In such systems, electrodes and electrolytes are integrated into the paper.

Due to their large surface areas and high conductivity, CNTs have been explored as attractive supercapacitor materials, using the electrochemical double layer mechanism.¹¹⁹ However, unmodified CNTs are hydrophobic, and their applications in supercapacitors have been hindered by poor electrolyte wetting.¹²⁴ Cellulose is highly water absorbent, which encourages the usage of conductive paper as electrodes for supercapacitors with aqueous electrolytes. By using cellulose, the aqueous electrolyte can be readily absorbed into the electrode and provides intimate contact between the electrode and the electrolyte.

In fuel cells, the chemical energy of a substrate, called fuel, is directly converted into electrical energy through an oxidation reaction between the fuel and an oxidant. Renewable fuels, such as hydrogen, ethanol, methane, *etc.*, can be used in fuel cells to produce electricity. A biofuel cell is a specific type of fuel cell that uses a biocatalyst (enzyme) or microorganisms to oxidize organic fuels, such as glucose, biomass, wastewater, *etc.* Biofuel cells are a clean energy alternative to both electrochemical batteries and conventional fuel cells that use expensive metal catalysts. Another advantage of biofuel cells is that they operate under mild pH and temperature conditions, compared to conventional fuel cells.

Fraiwan *et al.* reported on the first paper-based microbial fuel cells.^{139,140} Rapid generation of electricity was observed, while conventional MFCs require long start-up times (typically several days to a week). This observation is attributed to the hydrophilicity of the cell, which provides accumulation and acclimation of bacteria on the MFC anode.¹³⁹ Lee and Choi developed a 3-D paper-based bacteria-powered battery.¹²¹ They claimed that this battery can offer on-board energy to the next generation of paper-based systems with one drop of liquid derived from contaminant water and/or

wastewater sources. Paper-based biofuel cells are a easy-to-use power source. However, their low power generation and short-term stability make them be preferred only for low power and/or single use applications. For instance, they are a perfect power source for paper diagnostic devices. The papers used in the biofuel cells also require to be sophisticatedly patterned for microfluidic channels. Figure 3 illustrates the fully assembled paper-based MFC and its different layers.

Nanogenerators can convert a tiny scale of mechanical energy received into electricity. For example, they can generate electricity from a gentle airflow or human activity (like walking, reading, typing, *etc.*).¹³⁵ One marvelous application of nanogenerators is fabricating self-powered systems and active sensors.¹⁴¹ Paper-based nanogenerators (PNG) are attractive for building low-cost, green and disposable self-powered devices and systems.^{141,143} PNGs work based on the electrostatic effect. The electrostatic charges on the paper are generated by the corona method.¹⁴² Zhong *et al.* indicated that at a voltage of 110 V, the instantaneous output power density of a single-layered PNG can reach nearly 91 μ Wcm⁻².¹⁴² This power is sufficient to illuminate 70 LEDs instantaneously. They also fixed the PNG to a book and the energy of turning the pages lighted up two blue LEDs connected in antiparallel configuration. Kim *et al.*¹⁴¹ fabricated a foldable and thermally stable paper nanogenerator that included piezoelectrically active ZnO nanorods (Fig. 4 a). This paper-based nanogenerator was more thermally stable than the nanogenerator fabricated using polyethylene naphthalate (Fig. 4 b, c).



Figure 3: (a) A photograph of fully assembled paper-based MFC; (b) Different layers in paper-based MFC (with permission)¹²⁹



Figure 4: (a) A depiction of a paper-based generator with ZnO nanorods on a foldable cellulose paper; (b) A paper-based nanogenerator; (c) A polyethylene naphthalate nanogenerator (with permission)¹⁴¹

Smart materials (sensors and actuators)

A sensor is a type of electronic device applied for detecting some kind of stimulus instantaneously. The stimulus may be a change of temperature, pH, light, pressure, humidity and/or chemical or biological compounds. Sensors are broadly utilized in our daily life, ranging from lab-on-a-chip devices to condition monitoring of appliances and protection of natural and synthetic environments. A sensor is fundamentally a transducer that generates a measurable response proportional to a change in a physical, chemical, or biological condition. A sensor is composed of two main parts: a receptor and a transducer. Receptors can detect any stimulus, while transducers change the stimulus to an electric signal.

The most important properties of a sensor include its sensitivity, selectivity, reproducibility, stability, linearity, and scalability. Other characteristics of a sensor, such as response time, spatial and temporal resolution, hysteresis, creep and aging, are also considered. Most of the properties named here depend on the characteristics of the material used in sensors. Accordingly, an appropriate selection of the sensing material is a prerequisite for the desired performance of a sensor. Sensors are basically fabricated using two different sources of materials: inorganic semiconductors, usually metal oxides, or organic conducting polymers. However, both materials have some advantages and limitations. Inorganic semiconductors are generally unstable because of the ionic conducting charge on the surface. Their working temperature is high, which results in high energy consumption and latent safety concerns.⁹⁴ Organic materials that have a free electron on their double bond along the polymer main chain are appropriate for applications at ambient temperatures. However, they are not thermally stable and show very long response time.⁹⁴ To resolve the limitations and drawbacks of each material, various research has been conducted to enhance the sensor ability and flexibility. Conductive composites are now extensively under study to optimize their characteristics in terms of both sensing ability and intrinsic properties, importantly mechanical and thermal stability. Conductive polymers filled with NC show higher elongation at break, tensile modulus, and strength than unfilled films.

Conductive papers, also called "smart papers" have recently attracted great interest to be used as an active material in sensors and actuators.^{5,102,144-151} Similarly to sensors, an actuator is also a transducer, but it works differently. Actuators accept an electrical signal and take physical action. Smart papers have indicated good mechanically adaptive behavior in response to different stimuli. A promising characteristic of smart papers used as active sensors is that they are self-powered systems.^{139,142,152-153}

Yan and co-authors have developed smart papers to be used in strain sensors, where resistance varies with any mechanical stimulus, like force, pressure, tension, weight, *etc*.¹⁵⁴⁻¹⁵⁵ Such sensors have broad applications in mobile health monitoring, robotics and vibration control applications. The reason is they can be integrated into micro-electromechanical systems (MEMS) or be used in other electric devices, like micro-actuators. Smart papers have been also successfully applied in controlled drug delivery systems, where an electro-stimulated targeted system is used,¹⁵⁶⁻¹⁵⁸ or as a biosensor in detection systems.^{159,160} Other examples of smart paper used in sensing applications include humidity sensors,¹⁶¹ detecting explosives in aqueous solution,¹⁵² piezoelectric sensors,¹⁶² and tracing heavy metals or pollutants.¹⁶³

Transparent sheets

Generally, cellulose-based products are opaque; however, nanocellulose-based papers are transparent.^{33,122,124,164-169} Nanocellulose, due to its diameters being less than one-tenth of the visible light wavelength, avoid light scattering and, if the they packed densely, the tiny interstices between the nanoelements also avoid light scattering, and thus the cellulosic material becomes transparent. These outstanding characteristics offer the possibility of obtaining paper-based materials with high transparency and thermal stability similar to those of glass, while being lightweight and flexible as regular paper.

Tin-doped indium oxide (ITO) is generally used as a transparent electrode for optoelectronics. However, it is not mechanically resistant and easily cracks, which causes the malfunction of devices.¹¹⁹ Researchers are seeking to fabricate stronger and flexible transparent electrodes by using nanostructures. The low thermal expansion of transparent papers, with their high strength and modulus, combined with their flexibility, make them perfect for fabricating flexible transparent electronics and optoelectronics devices. Such devices, in which roll-to-roll processing is used, include conductive transparent electrodes for solar cells, display devices and organic light-emitting diodes

(OLEDs). It is worth mentioning that the optical properties of a paper-based electrode, including ISO brightness and opacity, as well as specific scattering, depend not only on the dimensions of the cellulose nanostructures, their morphology and crystallinity, but also on the method they are packed.¹²⁴

Insulation materials

Cellulose-based materials were once traditionally used as insulating cover for electrical components, like cables and capacitors. However, because of the hygroscopicity and poor mechanical resistance of cellulosic coatings, plastic materials have replaced them. The hygroscopic and mechanical properties of cellulosic materials depend on both the degree of cellulose crystallinity and its porosity.¹⁷⁰ The higher the degree of crystallinity and the porosity of cellulose, the less water sorption is observed. The water sorption properties of a paper-based component significantly affect its characteristics.¹⁷¹⁻¹⁷² The hydrophilic nature of NC can also be regulated by chemical modification or functionalization of the nanocelluloses. Some techniques that can reduce the hygroscopicity of the cellulosic material are graft polymerization, free radical polymerization,^{173,174} alkylation, acetylation,¹⁶⁸ carbanylation,¹⁷⁵ esterification,¹⁷⁸ using a hydrophobic coating of the paper,¹⁷⁷ and adsorption of cationic surfactants.¹⁰¹ The dielectric properties of a cellulosic compound also depend on other factors, including impurities, the content of hemicelluloses and lignin, the degree of polymerization, fiber length, and density.¹⁷¹

Oil impregnated paper is a reliable electrically insulating material in high voltage, high-power applications. Besides the cellulose availability and its low cost, the traditional exploitation of oil-impregnated paper is justified by some of its properties, such as high resistivity ($\sim 10^{10} \Omega \text{cm}^{-1}$), high electrical strength ($\sim 180 \text{ kV cm}^{-1}$ in oil), chemical stability, flexibility and non-thermoplastic properties.¹⁷¹ Improved mechanical characteristics of paper make it suitable for long-term use in electrical transformers, which is still in demand. The insulating property of paper should be considered not only for its use in electronics and electrical applications. Due to its transparency, paper-based coatings can have an outstanding application as thermal and/or sound insulators. It is expected that such a transparent coating on a window can not only save energy, but also act as a sound insulator for the building. Table 2 summarizes the reported data about the paper-based energy storage devices in the literature. The data include the source of the cellulose used, the composition of nanocomposites, the preparation method and application.

CHALLENGES AND FUTURE PROSPECTS

Nowadays, NC is considered a most promising green material and a future alternative for replacing the currently used synthetic materials. However, there are some challenges in the way of commercialization of paper-based devices. These challenges are related to the production of nanocellulose and the fabrication of paper-based devices, as described below.

The most important issue is designing an economical and sustainable process for continuous and large-scale production of nanocellulose. In this way, regulation and standardization of the product and production method are essential.

In addition to the production issues, the performance of electronic and electrical paper-based energy devices strongly depends on the controlled structure of the NC produced. There is a direct relationship between the structure, porosity, dimensions and surface properties of the nanocellulose and its behaviors. Accordingly, controlling these characteristics is crucial for obtaining the advantage of using nanocellulose-based components in high-performance energy storage devices. Controlling the size, morphology and polymorphism of cellulose during production and treatment is challenging, because it relies on deep understanding of the NC structure at atom scale.

More challenges are related to the fabrication of paper-based devices. It is quite challenging to fabricate thin, lightweight and flexible paper-based devices, while preserving their high mechanical strength and appropriate electronic characteristics.

Turna of callulosa	Draduat composition	Propagation mathed	Application	Dof
Type of centilose	Product composition	Preparation method	Application	Rel.
Soft wood kraft	TEMPO-oxidized cellulose	Cast coating of	Touch panel and	100
pulp	nanofibrils (TOCN)	CNT/TOCN	printed electronic	122
r r			application	
Cellulose	Cellulose/CNT	Printing	Batteries and	134
centulose		Timing	supercapacitors	
Cladonhora	Polymyrrolo/nanocalluloso/	Moulding	Storage devices for	136
ciuuopnoru	rorypymole/nanocenulose/		high-power	
centulose	carbon noer		applications	
Bleached	Carbon/impregnated paper with	Q 1 '. 1.'	Microbial fuel cells	139
cellulose fiber	sodium polysterene sulfonate	Sandwiching		
	Metal (ZnO, Au, Al) coated	~	Nanogenerators	141
Paper	cellulose	Spin coating		
		Thermal evaporation/	Nanogenerators	142
Paper	Polyterauoroethylene-Ag-paper	spin coating		
	Transparent paper/polystryrene			
Cellulose	sulfonate/ polylactic acid	Spin coating	Nanogenerators	143
	Glassy carbon/ethylene	Electro-	Microfluidic	
Filter paper	dioxythiophene	polymerization	sampling	145
Cladophora	uloxyulloplelle	Blending/sonication/	Lead II sensor	146
cellulose	Polyanaline/cellulose	filtering/drying		
Commercial		intering/drying		
nanoaalluloso	Graphene/nanocellulose	NR	Strain sensor	154
nanocenulose	Contron blook/poturol			
Cotton fiber		Blending/casting	Strain sensor	155
NC: (11)				
Microcrystalline	Cellulose nanocrystal/	Blending/oven drying	Humidity sensor	161
cellulose	graphene oxide	6 9 6	5	
Bacterial	Silver coated polyethylene	Sandwiching	Piezoelectric sensor	162
cellulose	terephthalate/bacterial cellulose	2		
Bleached	Cyanobacterial	Immobilization	Copper, iron sensor	163
softwood pulp	C-phycocyanin/nanocellulose			102
Pure cotton nuln	Modified graphene oxide/	Layer-by-layer	Proximity sensor	16/
i ure conton puip	cellulose nanocrystal	spraying		104
Bleached	Cladonhong		Electrical insulator	
sulphite		Blending/drying		171
softwood pulp	centriose/nanocentriose			
Commercial	NT	D1		170
nanocellulose	Nanocenulose/paper	Biending/not pressing	Electrical insulator	1/2

 Table 2

 Paper-based energy storage devices reported in the literature

Great efforts are conducting to resolving the mentioned problems, in parallel to designing and fabricating novel products, such as hierarchical 3D fibrous porous components, miniaturized analytical platforms, optical sensing-based electronics and wearable electronic devices. The future prospect of such efforts is paving the path for developing commercial applications of paper-based devices.

CONCLUSION

Cellulose is widely distributed in plants and, to a lesser degree, in invertebrates and microorganisms. Cellulose derived from invertebrates and bacteria is free from lignin, pectin and hemicelluloses, which are commonly present in the cellulose extracted from plants. However, the cost of the cellulose obtained from bacteria or invertebrates is quite high, thus limiting its applications.

Plant NC is obtained *via* different methods of mechanical, chemical and biochemical treatments. The mechanical and biochemical treatments to produce NC are more sustainable than chemical treatments. However, biochemical methods are restricted by the high cost of enzymes, while mechanical methods are confined by their high-energy consumption. Accordingly, a combination of treatments is suggested for commercial production of NC.

Due to its outstanding properties, NC has been widely considered for the development of highperformance energy devices, including batteries, supercapacitors, nanogenerators, sensors and transducers, as well as 3D energy textiles. These energy devices have demonstrated superior performance and unique properties, such as being stretchable and flexible, compared to equivalent traditional conductors. Such marvelous characteristics of these devices are strongly linked to the unique properties of the paper or textile used. Consequently, cellulose nanostructures provide new functionalities that bring a great opportunity for paper producers to develop new value-added products. Nevertheless, there are some challenges in the way of commercialization of paper-based electronic and electrical devices, in which NC is used. The most important one is the industrial scale NC production, ensuring the robustness and scalability of the process for mass production of NC. Besides, regulation and standardization of the product are essential for commercialization of the NC applications. In addition to the production issues, the performance of electronic and electrical paper-based energy devices strongly depends on the controlled structures of the NC produced. In other words, protecting the morphology and polymorphism of cellulose during treatment is challenging, which triggers further investigations.

REFERENCES

¹ Report "Cellulose Fiber Market", https://www.marketsandmarkets.com/PressReleases/cellulose-fiber.asp

² J. Y. R. Zhu, R. Sabo and X. Luo, *Green Chem.*, **13**, 1339 (2011), http://dx.doi.org/10.1039/c1gc15103g

³ J. Sadhukhan, J. R. Lloyd, K. Scott, G. C. Premier, H. Y. Eileen *et al.*, *Renew. Sustain. Energ. Rev.*, **56**, 116 (2016), https://doi.org/10.1016/j.rser.2015.11.015

⁴ G. P. Robertson, S. K. Hamilton, B. L. Barham, B. E. Dale, R. C. Izaurralde *et al.*, *Science*, **356**, 2324 (2017), https://doi.org/10.1126/science.aal2324

⁵ D. Tobjörk and R. Österbacka, Adv. Mater., 23, 1935 (2011), https://doi.org/10.1016/j.cep.2012.07.007

⁶ L. Brinchi, F. Cotana, E. Fortunati and J. M. Kenny, *Carbohyd. Polym.*, **94**, 154 (2013), https://doi.org/10.1016/j.carbpol.2013.01.033

⁷ J. L. Wertz, J. P. Mercier and O. Bédué, "Cellulose Science and Technology", CRC Press, (2010), https://www.crcpress.com/Cellulose-Science-and-Technology/Wertz-Mercier-Bedue/p/book/9780429131202

⁸ I. A. Sacui, R. C. Nieuwendaal, D. J. Burnett, S. J. Stranick, M. Jorfi *et al.*, *ACS Appl. Mater. Interfaces.*, **6**, 6127 (2014), https://doi.org/10.1021/am500359f

⁹ W. Chen, H. Yu, Y. Liu, Y. Hai, M. Zhang *et al.*, *Cellulose*, **18**, 433 (2011), https://doi.org/10.1007/s10570-011-9497-z

¹⁰ D. Klemm, B. Heublein, H. P. Fink and A. Bohn, *Angew. Chem. Int. Ed.*, **44**, 3358 (2005), https://doi.org/10.1002/anie.200460587

¹¹ J. I. Moran, V. A. Alvarez, V. P. Cyras and A. Vázquez, *Cellulose*, **15**, 149 (2008), https://doi.org/10.1007/s10570-007-9145-9

¹² F. Fahma, S. Iwamoto, N. Hori, T. Iwata and A. Takemura, *Cellulose*, **18**, 443 (2011), https://doi.org/10.1007/s10570-010-9480-0

¹³ D. Trache, M. H. Hussin, M. M. Haafiz and V. K. Thakur, *Nanoscale*, **9**, 1763 (2017), https://doi.org/10.1039/C6NR09494E

¹⁴ M. Gama, P. Gatenholm and D. Klemm (Eds.), "Bacterial Nanocellulose: A Sophisticated Multifunctional Material", CRC Press, 2012, https://www.crcpress.com/Bacterial-NanoCellulose-A-Sophisticated-Multifunctional-Material/Gama-Gatenholm-Klemm/p/book/9781138073166

¹⁵ M. Iguchi, S. Yamanaka and A. Budhiono, *J. Mater. Sci.*, **35**, 261 (2000), https://doi.org/10.1023/A:1004775229149

¹⁶ H. El-Saied, A. H. Basta and R. H. Gobran, *Polym. Plast. Technol. Eng.*, **43**, 797 (2004), https://doi.org/10.1081/PPT-120038065

¹⁷ R. M. Brown, *Abstr. Pap. Am. Chem. Soc.*, **227**, U303 (2004)

¹⁸ B. M. Cherian, A. L. Leao, S. F. de Souza, S. Thomas, L. A. Pothan *et al.*, in "Cellulose Fibers: Bio- and Nano-Polymer Composites", Springer, Berlin, Heidelberg, 2011, p. 539, https://doi.org/10.1007/978-3-642-17370-7_21

¹⁹ A. Retegi Miner, R. Zuluaga Gallego, P. Gañán Rojo and I. Mondragon, in "Cellulose Based Composites", Wiley-VCH Verlag GmbH, 2014, p. 63, https://doi.org/10.1002/9783527649440.ch4

²⁰ T. Heinze, in "Cellulose Chemistry and Properties: Fibers, Nanocelluloses and Advanced Materials", Springer International Publishing, 2016, pp. 1-52

²¹ M. M. Ruiz, J. Y. Cavaille, A. Dufresne, C. Graillat and J. F. Gérard, *Macromol. Symp.*, **169**, 211 (2001)

²² P. Sun, C. Sun and S. M. Weinreb, Org. Lett., 3, 3507 (2001), https://doi.org/10.1021/ol010179y

²³ K. Fleming, D. G. Gray and S. Matthews, *Chem. Eur. J.*, **7**, 1831 (2001), https://doi.org/10.1002/1521-3765(20010504)7:9<1831::AID-CHEM1831>3.0.CO;2-S ²⁴ S. M. Keshk and K. Sameshima, *Enzyme Microb. Technol.*, **40**, 4 (2006), https://doi.org/10.1016/j.enzmictec.2006.07.037

²⁵ J. Gong, J. Li, J. Xu, Z. Xiang and L. Mo, *RSC Adv.*, **7**, 33486 (2017), https://doi.org/10.1039/C7RA06222B

²⁶ J. Buffiere, N. Abad, P. Ahvenainen, J. Dou, M. J. Cocero *et al.*, ACS Sus. Chem. Eng., **2**, 16959 (2018), https://doi.org/10.1021/acssuschemeng.8b04296

²⁷ A. D. French, *Cellulose*, **1**, 885 (2014), https://doi.org/10.1007/s10570-013-0030-4

²⁸ K. Kafle, K. Greeson, C. Lee and S. H. Kim, *Text. Res. J.*, **84**, 1692 (2014), https://doi.org/10.1177/0040517514527379

²⁹ S. H. Kim, C. M. Lee and K. Kafle, *Korean J. Chem. Eng.*, **1**, 2127 (2013), https://doi.org/10.1007/s11814-013-0162-0

³⁰ C. M. Lee, A. Mittal, A. L. Barnette, K. Kafle and Y. B. Park, *Cellulose*, **20**, 991 (2013), https://doi.org/10.1007/s10570-013-9917-3

³¹ K. Kobayashi, S. Kimura, E. Togawa and M. Wada, *Carbohyd. Polym.*, **83**, 483 (2011), https://doi.org/10.1016/j.carbpol.2010.08.006

³² J. Li, X. Wei, Q. Wang, J. Chen, G. Chang *et al.*, *Carbohyd. Polym.*, **90**, 1609 (2012), https://doi.org/10.1016/j.carbpol.2012.07.038

³³ I. Siro, D. Plackett, M. Hedenqvist, M. Ankerfors and T. Lindström, J. Appl. Polym. Sci., **119**, 2652 (2011), https://doi.org/10.1002/app.32831

³⁴ Y. Davoudpour, S. Hossain, H. A. Khalil, M. M. Haafiz, Z. M. Ishak *et al.*, *Ind. Crop. Prod.*, **74**, 381 (2015), https://doi.org/10.1016/j.indcrop.2015.05.029

³⁵ M. Pääkkö, M. Ankerfors, H. Kosonen, A. Nykänen, S. Ahol *et al.*, *Biomacromolecules*, **8**, 1934 (2007), https://doi.org/10.1021/bm061215p

³⁶ A. Kaushik and M. Singh, *Carbohyd. Res.*, **346**, 76 (2011), https://doi.org/10.1016/j.carres.2010.10.020

³⁷ M. L. Hassan, A. P. Mathew, E. A. Hassan, N. A. El-Wakil and K. Oksman, *Wood Sci. Technol.*, **46**, 193 (2012), https://doi.org/10.1007/s00226-010-0373-z

³⁸ G. Han, S. Huan, J. Han, Z. Zhang and Q. Wu, *Materials*, **7**, 16 (2013), https://doi.org/10.3390/ma7010016

³⁹ N. R. Savadeka, V. S. Karande, N. Vigneshwaran, P. G. Kadam and S. T. Mhaske, *Appl. Nanosci.*, **5**, 281 (2015), https://doi.org/10.1007/s13204-014-0316-3

⁴⁰ A. Ferrer, I. Filpponen, A. Rodríguez, J. Laine and O. J. Rojas, *Bioresour. Technol.*, **125**, 249 (2012), https://doi.org/10.1016/j.biortech.2012.08.108

⁴¹ W. Wan, M. D. Mozuch, R. C. Sabo, P. Kersten, J. Y. Zhu *et al.*, *Cellulose*, **22**, 351 (2015), https://doi.org/10.1007/s10570-014-0465-2

⁴² G. Siqueira, S. Tapin-Lingua, J. Bras, D. da Silva Perez and A. Dufresne, *Cellulose*, **17**, 1147 (2010), https://doi.org/10.1007/s10570-010-9449-z

⁴³ T. Taniguchi and K. Okamura, *Polym. Int.*, **47**, 291 (1998), https://doi.org/10.1002/(SICI)1097-0126(199811)47:3<291::AID-PI11>3.0.CO;2-1

⁴⁴ M. Nuruddin, M. Hosur, M. Uddin, D. Baah and S. Jeelani, *J. Appl. Polym. Sci.*, **133**, 42990 (2016), https://doi.org/10.1002/app.42990

⁴⁵ L. Zhang, T. Tsuzuki and X. Wang, *Cellulose*, **2**, 1729 (2015), https://doi.org/10.1007/s10570-015-0582-6

⁴⁶ V. Baheti and J. Militky, *Fiber. Polym.*, **14**, 133 (2013), https://doi.org/10.1007/s12221-013-0133-4

⁴⁷ S. Iwamoto, A. N. Nakagaito and H. Yano, *Appl. Phys. A: Mater. Sci. Proc.*, **89**, 461 (2007), https://doi.org/10.1007/s00339-007-4175-6

⁴⁸ S. Janardhnan and M. Sain, *Bioresources*, **1**, 176 (2006), https://ojs.cnr.ncsu.edu/index.php/BioRes/article/view/BioRes_01_2_176_188_Janardnan_Sain_Isoluation_Cell ulose_Microfibrils_Enzymatic

⁴⁹ B. Wang and M. Sain, *Compos. Sci. Technol.*, **67**, 2521 (2007), https://doi.org/10.1016/j.compscitech.2006.12.015

⁵⁰ A. Alemdar and M. Sain, *Bioresour. Technol.*, **99**, 1664 (2008), https://doi.org/10.1016/j.biortech.2007.04.029

⁵¹ A. Chakraborty, M. Sain and M. Kortschot, *Holzforschung*, **59**, 102 (2005), https://doi.org/10.1515/HF.2005.016

⁵² H. P. Zhao, X. Q. Feng and H. Gao, *Appl. Phys. Lett.*, **90**, 073112 (2007), https://doi.org/10.1063/1.2450666
 ⁵³ Q. Cheng, S. Wang and T. G. Rials, *Compos. Part A: Appl. Sci. Manuf.*, **40**, 218 (2009),

https://doi.org/10.1016/j.compositesa.2008.11.009 ⁵⁴ S. Wang and Q. Cheng, J. Appl. Polym. Sci., **113**, 1270 (2009), https://doi.org/10.1002/app.30072

⁵⁵ P. Chen, H. Yu, Y. Liu, W. Chen, X. Wang *et al.*, *Cellulose*, **20**, 149 (2013), https://doi.org/10.1007/s10570-012-9829-7

⁵⁶ W. Li, R. Wang and S. Liu *BioResources*, **6**, 4271 (2011), https://bioresources.cnr.ncsu.edu/BioRes_06/BioRes_06_4_4271_Li_Wang_Liu_Nanocryst_Cell_SW_Kraft_Ul trasonic_Hydrol_1896.pdf

⁵⁷ S. P. Mishra, A. S. Manent, B. Chabot and C. Daneault, *BioResources*, **7**, 422 (2012), https://ojs.cnr.ncsu.edu/index.php/BioRes/article/view/BioRes_07_1_0422_Mishra_MCD_Prodn_Nanocellulose _Various_Options_Ultrasound

⁵⁸ W. Kamphunthong, P. Hornsby and K. Sirisinha, J. Appl. Polym. Sci., **125**, 1642 (2012), https://doi.org/10.1002/app.35642

⁵⁹ T. Kondo, R. Kose, H. Naito and W. Kasai, *Carbohyd. Polym.*, **112**, 284 (2014), https://doi.org/10.1016/j.carbpol.2014.05.064

⁶⁰ R. Kose, I. Mitani, W. Kasai and T. Kondo, *Biomacromolecules*, **12**, 716 (2011), https://doi.org/10.1021/bm1013469

⁶¹ A. Frenot, M. W. Henriksson and P. Walkenström, J. Appl. Polym. Sci., **103**, 1473 (2007), doi:10.1002/app.24912

⁶² H. Xu, Z. Li, D. Zhang, P. Hu and Z. Liu, J. Synth. Fiber. China, **9**, 004 (2006), https://doi.org/10.1002/app.24912

⁶³ K. Ohkawa, S. Hayashi, A. Nishida, H. Yamamoto and J. Ducreux, *Text. Res. J.*, **79**, 1396 (2009), https://doi.org/10.1177/0040517508101455

⁶⁴ M. G. Freire, A. R. Teles, R. A. Ferreira, L. D. Carlos, J. A. Lopes-da-Silva *et al.*, *Green Chem.*, **13**, 3173 (2011), https://doi.org/10.1039/C1GC15930E

⁶⁵ G. Viswanathan, S. Murugesan, V. Pushparaj, O. Nalamasu, P. M. Ajayan *et al.*, *Biomacromolecules*, **7**, 415 (2006), https://doi.org/10.1021/bm050837s

⁶⁶ S. L. Quan, S. G. Kang and I. J. Chin, *Cellulose*, **17**, 223 (2010), https://doi.org/10.1007/s10570-009-9386-x

⁶⁷ C. L. McCormick, P. A. Callais and B. H. Hutchinson, *Macromolecules*, **18**, 2394 (1987), https://doi.org/10.1021/ma00154a010

⁶⁸ A. Isogai, N. Mutoh, F. Onabe and M. Usuda, *Sen'iGakkaishi*, **45**, 299 (1989), https://doi.org/10.2115/fiber.45.7_299

⁶⁹ T. Rosenau, A. Potthast, I. Adorjan, A. Hofinger, H. Sixta *et al.*, *Cellulose*, **9**, 283 (2002), https://doi.org/10.1023/A:1021127423041

⁷⁰ J. Zhou, L. Zhang and J. Cai, J. Polym. Sci. Part B: Polym. Phys., **42**, 347 (2004), https://doi.org/10.1002/polb.10636

⁷¹ H. Zhang, J. Wu, J. Zhang and J. He, *Macromolecules*, **38**, 8272 (2005), https://doi.org/10.1021/ma0505676

⁷² S. Xu, J. Zhang, A. He, J. Li, H. Zhang *et al.*, *Polymer*, **49**, 2911 (2008), https://doi.org/10.1016/j.polymer.2008.04.046

⁷³ Z. Man, N. Muhammad, A. Sarwono, M. A. Bustam, M. V. Kumar *et al.*, *J. Polym. Environ.*, **19**, 726 (2011), https://doi.org/10.1007/s10924-011-0323-3

⁷⁴ S. K. Mahadeva, J. Kim and C. Jo, *Int. J. Precis. Eng. Manuf.*, **12**, 47 (2011), https://doi.org/10.1007/s12541-011-0006-y

⁷⁵ F. Hermanutz, F. Gähr, E. Uerdingen, F. Meister and B. Kosan, *Macromol. Symp.*, **262**, 23 (2008), https://doi.org/10.1002/masy.200850203

⁷⁶ C. W. Kim, D. S. Kim, S. Y. Kang, M. Marquez and Y. L. Joo, *Polymer*, **47**, 5097 (2006), https://doi.org/10.1016/j.polymer.2006.05.033

⁷⁷ B. M. Cherian, A. L. Leão, S. F. de Souza, S. Thomas, L. A. Pothan *et al.*, *Carbohyd. Polym.*, **81**, 720 (2010) https://doi.org/10.1016/j.carbpol.2010.03.046

⁷⁸ B. Deepa, E. Abraham, B. M. Cherian, A. Bismarck, J. J. Blaker *et al.*, *Bioresour. Technol.*, **102**, 1988 (2011), https://doi.org/10.1016/j.biortech.2010.09.030

⁷⁹ E. Abraham, B. Deepa, L. A. Pothan, M. Jacob, S. Thomas *et al.*, *Carbohyd. Polym.*, **86**, 1468 (2011), https://doi.org/10.1016/j.carbpol.2011.06.034

⁸⁰ A. Ashori, M. Babaee, M. Jonoobi and Y. Hamzeh, *Carbohyd. Polym.*, **102**, 369 (2014), https://doi.org/10.1016/j.carbpol.2013.11.067

⁸¹ R. Zuluaga, J. L. Putaux, J. Cruz, J. Vélez, I. Mondragon *et al.*, *Carbohyd. Polym.*, **76**, 51 (2009), https://doi.org/10.1016/j.carbpol.2008.09.024

⁸² M. F. Rosa, E. S. Medeiros, J. A. Malmonge, K. S. Gregorski, D. F. Wood *et al.*, *Carbohyd. Polym.*, **81**, 83 (2010), https://doi.org/10.1016/j.carbpol.2010.01.059

⁸³ A. C. Corrêa, E. Morais Teixeira, L. A. Pessan and L. H. Mattoso, *Cellulose*, **17**, 1183 (2010), https://doi.org/10.1007/s10570-010-9453-3

⁸⁴ H. Kargarzadeh, I. Ahmad, I. Abdullah, A. Dufresne, S. Y. Zainudin *et al.*, *Cellulose*, **19**, 855 (2012), https://doi.org/10.1007/s10570-012-9684-6

⁸⁵ N. Johar, I. Ahmad and A. Dufresne, *Ind. Crop. Prod.*, **37**, 93 (2012), https://doi.org/10.1016/j.indcrop.2011.12.016

⁸⁶ L. Ludueña, D. Fasce, V. A. Alvarez and P. M. Stefani, *BioResources*, **6**, 1440 (2011), https://ojs.cnr.ncsu.edu/index.php/BioRes/article/view/BioRes_06_2_1440_Luduena_FAS_Nanocellulose_Rice_Husk

⁸⁷ J. P. Morais, M. Freitas Rosa, L. D. Nascimento, D. M. Nascimento and A. R. Cassales, *Carbohyd. Polym.*, **91**, 229 (2013), https://doi.org/10.1016/j.carbpol.2012.08.010

⁸⁸ P. P. Zhang, D. S. Tong, C. X. Lin, H. M. Yang, Z. K. Zhong *et al.*, *Asia-Pacific J. Chem. Eng.*, **9**, 686 (2014), https://doi.org/10.1002/apj.1812

⁸⁹ V. Kokol, M. Božič, R Vogrinčič and A. P. Mathew, *Carbohyd. Polym.*, **125**, 301 (2015), https://doi.org/10.1016/j.carbpol.2015.02.056

⁹⁰ S. Camarero Espinosa, T. Kuhnt, E. J. Foster and C. Weder, *Biomacromolecules*, **14**, 1223 (2013), https://doi.org/10.1021/bm400219u

⁹¹ S. Li, C. Li, M. Yan, Y. Wu, J. Cao *et al.*, *Polym. Degrad. Stabil.*, **98**, 1940 (2013), https://doi.org/10.1016/j.polymdegradstab.2013.06.017

⁹² H. Sadeghifar, I. Filpponen, S. P. Clarke, D. F. Brougham and D. S. Argyropoulos, *J. Mater. Sci.*, **46**, 7344 (2011), https://doi.org/10.1007/s10853-011-5696-0

⁹³ H. Yu, Z. Qin, B. Liang, N. Liu, Z. Zhou *et al.*, *J. Mater. Chem.*, **A1**, 3938 (2013), https://doi.org/10.1039/C3TA01150J

⁹⁴ P. B. Filson, B. E. Dawson-Andoh and D. Schwegler-Berry, *Green Chem.*, **11**, 1808 (2009), https://doi.org/10.1039/B915746H

⁹⁵ R. Zuluaga, J. L. Putaux, A. Restrepo, I. Mondragon and P. Gañán, *Cellulose*, **14**, 585 (2009), https://doi.org/10.1007/s10570-007-9118-z

⁹⁶ F. Jiang and Y. L. Hsieh, *Carbohyd. Polym.*, **95**, 32 (2013), https://doi.org/10.1016/j.carbpol.2013.02.022

⁹⁷ F. Tao, H. Song and L. Chou, *Carbohyd. Res.*, **346**, 58 (2011), https://doi.org/10.1016/j.carres.2010.10.022

⁹⁸ T. Saito, Y. Nishiyama, J. L. Putaux, M. Vignon and A. Isogai, *Biomacromolecules*, **7**, 1687 (2006), https://doi.org/10.1021/bm060154s

⁹⁹ M. Hirota, N. Tamura, T. Saito and A. Isogai, *Cellulose*, **17**, 279 (2010), https://doi.org/10.1007/s10570-009-9381-2

¹⁰⁰ S. Iwamoto, A. Isogai and T. Iwata, *Biomacromolecules*, **12**, 831 (2011), https://doi.org/10.1021/bm101510r

¹⁰¹ K. Xhanari, K. Syverud, G. Chinga-Carrasco, K. Paso and P. Stenius, *Cellulose*, **18**, 257 (2011), https://doi.org/10.1007/s10570-010-9482-y

¹⁰² S. Ummartyotin and H. Manuspiya, *Renew. Sustain. Energ. Rev.*, **41**, 402 (2015), https://doi.org/10.1016/j.rser.2014.08.050

¹⁰³ M. Henriksson, G. Henriksson, L. A. Berglund and T. Lindström, *Eur. Polym. J.*, **43**, 3434 (2007), https://doi.org/10.1016/j.eurpolymj.2007.05.038

¹⁰⁴ P. B. Filson and B. E. Dawson-Andoh, *Bioresour. Technol.*, **100**, 2259 (2009), https://doi.org/10.1016/j.biortech.2008.09.062

¹⁰⁵ D. Mikkelsen, B. M. Flanagan, G. A. Dykes and M. J. Gidley, *J. Appl. Microbiol.*, **107**, 576 (2009), https://doi.org/10.1111/j.1365-2672.2009.04226.x

¹⁰⁶ T. Ishida, Y. Sugano, T. Nakai and M. Shoda, *Biosci. Biotechnol. Biochem.*, **66**, 1677 (2002), https://doi.org/10.1271/bbb.66.1677

¹⁰⁷ C. Castro, R. Zuluaga, J. L. Putaux, G. Caro, I. Mondragon *et al.*, *Carbohyd. Polym.*, **84**, 96 (2011), https://doi.org/10.1016/j.carbpol.2010.10.072

¹⁰⁹ D. Kralisch, N. Hessler, M. Munteanu, B. Sultanova, D. Klemm *et al.*, *Abstr. Pap. Am. Chem. Soc.*, **241** (2011)

¹¹⁰ A. Krystynowicz, W. Czaja, A. Wiktorowska-Jezierska, M. Gonçalves-Miśkiewicz, M. Turkiewicz *et al.*, *J. Ind. Microbiol. Biotechnol.*, **29**, 189 (2002), https://doi.org/10.1038/sj.jim.7000303

¹¹¹ S. Kongruang, *Appl. Biochem. Biotechnol.*, **148**, 245 (2008), https://doi.org/10.1007/978-1-60327-526-2_70
 ¹¹² K. Watanabe, M. Tabuchi, Y. Morinaga and F. Yoshinaga, *Cellulose*, **5**, 187 (1998), https://doi.org/10.1023/A:1009272904582

¹¹³ P. G. Verschuren, T. D. Cardona, M. R. Nout, K. D. De Gooijer and J. C. Van den Heuvel, *J. Biosci. Bioeng.*, **89**, 414 (2000), https://doi.org/10.1016/S1389-1723(00)89089-1

¹¹⁴ H. Kornmann, P. Duboc, I. Marison and U. Von Stockar, *Appl. Environ. Microbial.*, **69**, 6091 (2003), https://doi.org/10.1128/AEM.69.10.6091-6098.2003

¹¹⁵ E. P. Çoban and H. Biyik, Afr. J. Microbiol. Res., 5, 1037 (2011), https://doi.org/10.5897/AJMR11.008

¹¹⁶ W. Chen, H. Yu, S. Y. Lee, T. Wei, J. Li et al., Chem. Soc. Rev., **47**, 2837 (2018), https://doi.org/10.1039/C7CS00790F

¹¹⁷ B. K. Deka, A. Hazarika, J. Kim, Y. B. Park and H. W. Park, Int. J. Energ. Res., 41, 1397 (2017), https://doi.org/10.1002/er.3707

¹¹⁸ A. Dufresne, "Nanocellulose: From Nature to High Performance Tailored Materials", Walter de Gruyter GmbH, 2017, https://doi.org/10.1515/9783110254600

¹¹⁹ L. Hu and Y. Cui, *Energ. Environ. Sci.*, **5**, 6423 (2012), https://doi.org/10.1039/C2EE02414D

¹²⁰ L. Hu, N. Liu, M. Eskilsson, G. Zheng, J. McDonough *et al.*, *Nano Energ.*, **2**, 1385 (2013), https://doi.org/10.1016/j.nanoen.2012.08.008

¹²² H. Koga, T. Saito, T. Kitaoka, M. Nogi, K. Suganuma et al., Biomacromolecules, 14, 1160 (2013), https://doi.org/10.1021/bm400075f

¹²³ X. Wu, F. Zhao, J. R. Varcoe, A. E. Thumser, C. Avignone-Rossa *et al.*, *Bioelectrochemistry*, **77**, 64 (2009), https://doi.org/10.1016/j.bioelechem.2009.05.008

¹²⁴ G. Zheng, Y. Cui, E. Karabulut, L. Wågberg, H. Zhu *et al.*, *MRS Bull.*, **38**, 320 (2013), https://doi.org/10.1557/mrs.2013.59

¹²⁵ Z. Weng, Y. Su, D. W. Wang, F. Li, J. Du *et al.*, *Adv. Energ. Mater.*, **1**, 917 (2011), https://doi.org/10.1002/aenm.201100312

¹²⁶ X. Chen, H. Lin, P. Chen, G. Guan, J. Deng *et al.*, *Adv. Mater.*, **26**, 4444 (2014), https://doi.org/10.1002/adma.201400842

¹²⁷ B. Dyatkin, V. Presser, M. Heon, M. R. Lukatskaya, M. Beidaghi *et al.*, *Chem. Sus. Chem.*, **6**, 2269 (2013), https://doi.org/10.1002/cssc.201300852

¹²⁸ T. Chen and L. Dai, J. Mater. Chem., A2, 10756 (2014), https://doi.org/10.1039/C4TA00567H

¹²⁹ Z. Gui, H. Zhu, E. Gillette, X. Han, G. W. Rubloff *et al.*, ACS Nano, **7**, 6037 (2013), https://doi.org/10.1021/nn401818t

¹³⁰ L. Bao and X. Li, Adv. Mater., 24, 3246 (2012), https://doi.org/10.1002/adma.201200246

- ¹³¹ K. Jost, G. Dion and Y. Gogotsi, J. Mater. Chem., A2, 10776 (2014), https://doi.org/10.1039/C4TA00203B
- ¹³² U. Gulzar, F. De Angelis, R. P. Zaccaria and C. Capiglia, *World J. Text. Eng. Technol.*, **2**, 6 (2016), https://pdfs.semanticscholar.org/ae87/6e0fd4da01817aac1e51e3ce35a9ff4de1cb.pdf

¹³³ S. Zhai, H. E. Karahan, L. Wei, Q. Qian, A. T. Harris *et al.*, *Energ. Storage Mater.*, **3**, 123 (2016), https://doi.org/10.1016/j.ensm.2016.02.003

¹³⁴ L. Hu, H. Wu and Y. Cui, *Appl. Phys. Lett.*, **96**, 183502 (2010), https://doi.org/10.1063/1.3425767

¹³⁵ S. Hu, R. Rajamani and X. Yu, Appl. Phys. Lett., **100**, 104103 (2012), https://doi.org/10.1063/1.3691948

¹³⁶ A. Razaq, L. Nyholm, M. Sjödin, M. Strømme and A. Mihranyan, Adv. Energ. Mater., **2**, 445 (2012), https://doi.org/10.1002/aenm.201100713

¹³⁷ A. Chiappone, J. R. Nair, C. Gerbaldi, L. Jabbour, R. Bongiovanni *et al.*, J. Power Sources, **196**, 10280 (2011), https://doi.org/10.1016/j.jpowsour.2011.07.015

⁽¹⁾¹³⁸ A. Chiappone, F. Bella, J. R. Nair, G. Meligrana, R. Bongiovanni *et al.*, *Chem. Electro Chem.*, **1**, 1350 (2014), https://doi.org/10.1002/celc.201402051

¹³⁹ A. Fraiwan, S. Mukherjee, S. Sundermier, H. S. Lee and S. Choi, *Biosens. Bioelectron.*, **49**, 410 (2013), https://doi.org/10.1016/j.bios.2013.06.001

¹⁴⁰ A. Fraiwan, H. Lee and S. Choi, *IEEE Sens. J.*, **14**, 3385 (2013), https://doi.org/10.1109/JSEN.2014.2332075
 ¹⁴¹ K. H. Kim, K. Y. Lee, J. S. Seo, B. Kumar and S. W. Kim, *Small*, **7**, 2577 (2011), https://doi.org/10.1002/smll.201100819

¹⁴² Q. Zhong, J. Zhong, B. Hu, Q. Hu, J. Zhou *et al.*, *Energ. Environ. Sci.*, **6**, 1779 (2013), https://doi.org/10.1039/C3EE40592C

¹⁴³ X. Gao, L. Huang, B. Wang, D. Xu, J. Zhong *et al.*, ACS Appl. Mater. Interfaces, **8**, 35587 (2016), https://doi.org/10.1021/acsami.6b12913

¹⁴⁴ A. Khan, Z. Abas, H. S. Kim and J. Kim, *Sensors*, **16**, 1172 (2016), https://doi.org/10.3390/s16081172

¹⁴⁵ R. Ding, V. Krikstolaityte and G. Lisak, *Sensors Actuators B: Chem.*, **290**, 347 (2019), https://doi.org/10.1016/j.snb.2019.03.079

¹⁴⁶ D. S. Tan, M. G. Impas, D. H. Camacho and S. T. Palisoc, *Cellulose Chem. Technol.*, **52**, 853 (2018), http://www.cellulosechemtechnol.ro/pdf/CCT9-10(2018)/p.853-861.pdf

¹⁴⁷ S. Parween and A. Asthana, *Sensors Actuators B: Chem.*, **15**, 405 (2019), https://doi.org/10.1016/j.snb.2019.01.064

¹⁴⁸ T. Zhou, J. J. Liu, Y. Xu and Z. Y. Wu, *Microchem. J.*, **1**, 703 (2019), https://doi.org/10.1016/j.microc.2018.10.022

¹⁴⁹ C. Puangbanlang, K. Sirivibulkovit, D. Nacapricha and Y. Sameenoi, *Talanta*, **1**, 542 (2019), https://doi.org/10.1016/j.talanta.2019.02.048

¹⁵⁰ F. Ciolacu, *Cellulose Chem. Technol.*, **52**, 863 (2018), http://www.cellulosechemtechnol.ro/pdf/CCT9-10(2018)/p.863-871.pdf

¹⁵¹ L. M. Fu and Y. N. Wang, Trends Anal. Chem., **107**, 196 (2018), https://doi.org/10.1016/j.trac.2018.08.018

¹⁵² X. Wang, Y. Guo, D. Li, H. Chen and R. C. Sun, *Chem. Commun.*, **48**, 5569 (2012), https://doi.org/10.1039/C2CC30208J

¹⁵³ L. Lin, Y. Hu, C. Xu, Y. Zhang, R. Zhang *et al.*, *Nano Energy*, **2**, 75 (2013), https://doi.org/10.1016/j.nanoen.2012.07.019 ¹⁵⁴ C. Yan, J. Wang, W. Kang, M. Cui, X. Wang *et al.*, *Adv. Mater.*, **26**, 2022 (2014), https://doi.org/10.1002/adma.201304742

¹⁵⁵ X. Wu, C. Lu, Y. Han, Z. Zhou, G. Yuan *et al.*, *Compos. Sci. Technol.*, **124**, 44 (2016), https://doi.org/10.1016/j.compscitech.2016.01.012

¹⁵⁶ M. Prabaharan and J. F. Mano, *Macromol. Biosci.*, **6**, 991 (2006), https://doi.org/10.1002/mabi.200600164

¹⁵⁷ Z. Zhang, L. Chen, C. Zhao, Y. Bai, M. Deng *et al.*, *Polymer*, **52**, 676 (2011), https://doi.org/10.1016/j.polymer.2010.12.048

¹⁵⁸ J. Xie and J. Li, J. Bioresour. Bioprod., **2**, 1 (2017), http://www.bioresourcesbioproducts.com/index.php/bb/article/view/125

¹⁵⁹ J. V. Edwards, N. Prevost, A. French, M. Concha, A. DeLucca *et al.*, *Engineering*, **5**, 20 (2013), https://doi.org/10.4236/eng.2013.59A003

¹⁶⁰ J. R. Navarro, S. Wennmalm, J. Godfrey, M. Breitholtz and U. Edlund, *Biomacromolecules*, **17**, 1101 (2016), https://doi.org/10.1021/acs.biomac.5b01716

¹⁶¹ A. Kafy, A. Akther, M. I. Shishir, H. C. Kim, Y. Yun *et al.*, *Sensors Actuators A: Phys.*, **247**, 221 (2016), https://doi.org/10.1016/j.sna.2016.05.045

¹⁶² R. K. Mangayil, S. M. Rajala, A. J. Pammo, E. L. Sarlin, J. Luo *et al.*, ACS Appl. Mater. Interfaces, 9, 19048 (2017), https://doi.org/10.1021/acsami.7b04927

¹⁶³ R. Weishaupt, G. Siqueira, M. Schubert, M. M. Kämpf, T. Zimmermann *et al.*, *Adv. Funct. Mater.*, **27**, 1604291 (2017), https://doi.org/10.1002/adfm.201604291

¹⁶⁴ K. K. Sadasivuni, A. Kafy, L. Zhai, H. U. Ko, S. Mun *et al.*, *Small*, **11**, 994 (2015), https://doi.org/10.1002/smll.201402109

¹⁶⁵ Y. Okahisa, A. Yoshida, S. Miyaguchi and H. Yano, *Compos. Sci. Technol.*, **69**, 1958 (2009), https://doi.org/10.1016/j.compscitech.2009.04.017

¹⁶⁶ H. Yano, J. Sugiyama, A. N. Nakagaito, M. Nogi, T. Matsuura *et al.*, *Adv. Mater.*, **17**, 153 (2005), https://doi.org/10.1002/adma.200400597

¹⁶⁷ S. Iwamoto, A. N. Nakagaito, H. Yano and M. Nogi, *Appl. Phys. A: Mater. Sci. Proc.*, **81**, 1109 (2005), https://doi.org/10.1007/s00339-005-3316-z

¹⁶⁸ H. Ono, Y. Shimaya, K. Sato and T. Hongo, *Polym. J.*, **36**, 684 (2004), https://doi.org/10.1295/polymj.36.684
 ¹⁶⁹ S. Ifuku, M. Nogi, K. Abe, K. Handa, F. Nakatsubo *et al.*, *Biomacromolecules*, **8**, 1973 (2007), https://doi.org/10.1021/bm070113b

¹⁷⁰ A. Mihranyan, A. P. Llagostera, R. Karmhag, M. Strømme and R. Ek, *Int. J. Pharm.*, **269**, 433 (2004), https://doi.org/10.1016/j.ijpharm.2003.09.030

¹⁷¹ D. Le Bras, M. Strømme and A. Mihranyan, *J. Phys. Chem. B*, **119**, 5911 (2015), https://doi.org/10.1021/acs.jpcb.5b00715

¹⁷²J. Huang, Y. Zhou, L. Dong, Z. Zhou and R. Liu, *Compos. Sci. Technol.*, **138**, 40 (2017), https://doi.org/10.1016/j.compscitech.2016.11.020

¹⁷³ K. Littunen, U. Hippi, L. S. Johansson, M. Österberg, T. Tammelin *et al.*, *Carbohyd. Polym.*, **84**, 1039 (2011), https://doi.org/10.1016/j.carbpol.2010.12.064

¹⁷⁴ P. Stenstad, M. Andresen, B. S. Tanem and P. Stenius, *Cellulose*, **15**, 35 (2008), https://doi.org/10.1007/s10570-007-9143-y

¹⁷⁵ G. Siqueira, J. Bras, N. Follain, S. Belbekhouche, S. Marais *et al.*, *Carbohyd. Polym.*, **91**, 711 (2013), https://doi.org/10.1016/j.carbpol.2012.08.057

¹⁷⁶ H. Yuan, Y. Nishiyama, M. Wada and S. Kuga, *Biomacromolecules*, **7**, 696 (2006), https://doi.org/10.1021/bm050828j

¹⁷⁷ J. T. Korhonen, M. Kettunen, R. H. Ras and O. Ikkala, *ACS Appl. Mater. Interfaces*, **3**, 1813 (2011), https://doi.org/10.1021/am200475b